What is Claimed:

- 1. An adhesive coated article comprising a substrate with a first and second major surface and a layer of microsphere adhesive on at least a portion of the first major surface of the substrate, wherein the microspheres of the microsphere adhesive are the reaction product of (a) at least one alkyl (meth)acrylate ester wherein the alkyl group contains four to about 14 carbon atoms and (b) at least one nonpolar, ionic, polar comonomer or mixtures of such comonomers.
- 2. The adhesive coated article according to claim 1 wherein the microsphere adhesive has 90° peel value, as measured on Kromkote® paper in the range of 20 to 250 grams/in.
- 3. The adhesive coated article according to claim 1 wherein component (b) is a (meth) acrylamide monomer.
- 4. The aghesive coated article according to claim 1 wherein the microsphere adhesive further includes 1-10% by weight of an aqueous polyacrylamide/material.

20

25

5

10

15

5. The adhesive coated article according to claim 1 wherein the microsphere adhesive comprises (a) a plurality of polymeric, solid, elastomeric microspheres that are the reaction product of reactants comprising polymerizable starting materials comprising at least one C_4 - C_{14} alkyl (meth)acrylate ester monomers and at least one (meth)acrylamide comonomer with the proviso that the polar comonomer has no dissociable proton having a K_d of greater than 10^{-3} , (b) a polymeric stabilizer in an amount of about 0.1 to about 3 parts by weight per 100 parts by weight of the microspheres, and (c) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres.

CM CA

5

10

15

6. The adhesive coated article according to claim 1 wherein the microsphere adhesive comprises (a) a plurality of polymeric, solid, elastomeric microspheres that are the reaction product of reactants comprising polymerizable starting materials comprising at least one C_4 - C_{14} alkyl (meth)acrylate ester monomers and at least one polar comonomer with the proviso that if the polar comonomer has a dissociable proton, the polar comonomer has no dissociable proton having a K_a of greater than 10^{-3} , (b) a polymeric stabilizer in an amount of about 0.1 to about 3 parts by weight per 100 parts by weight of the microspheres, and (c) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres

7. The adhesive coated article according to claim 1 wherein the microsphere adhesive comprises (a) a plurality of polymeric, clastomeric microspheres wherein the microspheres are the reaction product of polymerizable, starting materials comprising at least one C_4 - C_{14} alkyl (meth)acrylate ester monomer and at least one (meth)acrylamide comonomer, (b) an initiator for the polymerizable monomer starting materials present in amounts ranging from 0.1 to approximately 2 parts by weight per 100 part by weight of the polymerizable monomer starting materials, (c) optionally, a polymeric stabilizer in an amount of between about 0.1 and about 3 parts by weight per 100 parts by weight of the microspheres, (d) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres, and (e) a chain transfer agent in an amount sufficient to produce 30-98% of a solvent-soluble portion in the microspheres.

8. The adhesive coated article according to claim 7 further comprising (f) at least one vinyl-unsaturated additive having both an ionic moiety and a hydrophobic moiety and containing at least 5 but not more that 40 carbon atoms in an amount of about 0.1 to 3 parts by weight of the microspheres.

5

10

15

- 9. The adhesive coated article according to claim 4 wherein the microsphere adhesive comprises (a) a plurality of polymeric, elastomeric microspheres wherein the microspheres are the reaction product of polymerizable, starting materials comprising at least one C₄-C₁₄ alkyl (meth)acrylate ester monomer, (b) an initiator for the polymerizable monomer starting materials present in amounts ranging from 0.1 to approximately 2 parts by weight per 100 part by weight of the polymerizable monomer starting materials, (c) optionally, a polymeric stabilizer in an amount of between about 0.1 and about 3 parts by weight per 100 parts by weight of the microspheres, (d) a surfactant in an amount of no greater than about 5 parts by weight per 100 parts by weight of the microspheres, and (e) a chain transfer agent in an amount sufficient to produce 30-98% of a solvent-soluble portion in the microspheres.
- 10. The adhesive coated article according to claim 9 further comprising (f) at least one vinyl-unsaturated additive having both an ionic moiety and a hydrophobic moiety and containing at least 5 but not more that 40 carbon atoms in an amount of about 0.1 to 3 parts by weight of the microspheres.
- 11. The adhesive coated article according to claim 1 wherein the
 20 microsphere adhesive comprises a plurality of hollow, polymeric, acrylate,
 inherently tacky, infusible, solvent-insoluble, solvent dispersible, pressure sensitive
 microspheres comprising (a) at least about 85 parts by weight of at least one alkyl
 acrylate ester or alkyl methacrylate ester, and (b) up to about 15 parts by weight of
 at least one (meth)acrylamide monomer, wherein a majority of the microspheres
 25 contain at least one interior void having a diameter at least about 10% of the
 diameter of the hollow microspheres.
 - 12. The adhesive coated article according to claim 4 wherein the microsphere adhesive comprises a plurality of hollow, polymeric, acrylate, inherently tacky, infusible, solvent-insoluble, solvent dispersible, pressure sensitive

5

10

15

20

microspheres comprising (a) at least about 85 parts by weight of at least one alkyl acrylate ester or alkyl methacrylate ester, and (b) up to about 15 parts by weight of at least one polar monomer, wherein a majority of the microspheres contain at least one interior void having a diameter at least about 10% of the diameter of the hollow microspheres.

- 13. The adhesive coated article according to claim 4 wherein the microsphere adhesive comprises composite pressure sensitive adhesive microspheres comprising a mixture of two or more water insoluble polymers that are present wholly within the boundaries of the microspheres, wherein at least one water insoluble polymer is a solute polymer and at least one water insoluble polymer is a matrix polymer.
- 14. The adhesive coated article according to claim 1 wherein the microsphere adhesive comprises composite pressure sensitive adhesive microspheres comprising a mixture of two or more water insoluble polymers that are present wholly within the boundaries of the microspheres, wherein at least one water insoluble polymer is a solute polymer and at least one water insoluble polymer is a matrix polymer, and wherein the solute polymer is a homopolymer or copolymer prepared from (meth) acrylamide monomers.
- a low adhesion backsize coating on at least a portion of the second major surface, such that the low adhesion backsize coating is positioned directly under the microsphere adhesive layer on the first major surface, such that when at least two adhesive coated articles are stacked upon another, the microsphere adhesive layer of a first adhesive coated article is contiguously positioned on top of the low adhesion backsize/coating of a second adhesive coated article.